

IN THE SPECIFICATION

Please replace paragraph #2 on page 6 with the following paragraph.

Examples of the acryl monomer include acrylonitrile, acrylimide, diacetone acrylimide, methylacrylate, butylmethacrylate, laurylmethacrylate, acrylic acid, methylmethacrylate, ethylacrylate, butylacrylate, ethylmethacrylate, glycidyl methacrylate, 2-hydroxyethylmethacrylate, 2-hydroxyethylacrylate, hydroxypropylacrylate, etc. These can be used alone or in a mixture thereof. The acryl monomer undergoes a radical reaction at a temperature of about 80 to 140°C.